

# Design of Shallow Source/Drain Extension (SDE) Profiles in Improving Short-Channel Effect (SCE) in Nanoscale Devices

Mohd Hafiz Sulaiman, Anis Suhaila Mohd Zain, Ayuni Fateeha Muda and, Sani Irwan Md Salim  
Faculty of Electronic and Computer Engineering  
Universiti Teknikal Malaysia Melaka, Hang Tuah Jaya, 76100 Durian Tunggal, Melaka, Malaysia.  
mohdhafizbinsulaiman@gmail.com

**Abstract**—This paper purposed the design of shallow source/drain extension (SDE) in improving short channel effect (SCE) in nanoscale devices. In order to increase the mobility and the speed of the electronic devices, semiconductor technology researchers face the limitations such as short channel effect in MOSFET device as it is unavoidable in scaling. Thus, the aim of this project is to improve the short-channel effect in nanoscale devices. The design parameter standard structure of Metal-Oxide-Semiconductor Field-Effect Transistor (MOSFET) were proposed referring to the International Technology Roadmap for Semiconductors (ITRS) 2011 edition and compared the structure with same standard structure of ITRS with modification to the junction depth that becomes more shallow source/drain extension (SDE). Silvaco's DEVEDIT software is used to design the structure of MOSFET with three different gate lengths, while Silvaco's ATLAS software is used to simulate the structure for data extraction to obtain the output graph. From the output, it shows that, as the size of MOSFET gate length becomes smaller, the threshold voltages also decrease. In improving the SCE, the value of threshold voltage,  $V_{th}$ , is slightly increases on shallower the source/drain extension (SDE). The value of "ON" current ( $I_{ON}$ ) also has been extracted for all designs of MOSFET.

**Index Terms**—Short-Channel Effect (SCE); Shallow Source/Drain Extension (SDE); Nanoscale Devices; Silvaco.

## I. INTRODUCTION

For more than 30 years, the Metal - Oxide - Semiconductor Field-Effect Transistor (MOSFET) has continually been scale down in size in channel length from micrometers to sub-micrometers and then to sub-sub-micrometers range following Moore's Law. The channel length of MOSFET is reducing from 100nm to 45nm. The size reduction of the device makes great improvement to MOSFET operation. [1] However, there are many effects when reduction the scale size of the MOSFET. One of the effect is the short-channel effect [2].

Short-channel effect is an effect of the channel length of a MOSFET is the same order of magnitude as the depletion-layer widths of the source and drain junction and also behaves differently from other MOSFETs. There are two physical phenomenon of the short channel effect. The first is the limitation imposed on electron drift characteristics in channel and the second is the modification of the threshold voltage due to the shortening channel length [3]. In this project, the source/drain extension has been selected to be studied. The concept that influence for scaling the shallow source/drain extension (SDE) must be known for improving the short-

channel effect. Finally, the design of shallow source/drain extension is proposed.

## II. DEVICES DESIGN AND SIMULATE PROCESS

Development of this project is divided into two stages. The first stage is gathering the information, analyzing and research on short-channel effect (SCE). For this project, the most important part is to design the shallow source/drain extension which is scaling the junction depth of MOSFET. All data and information collected is used when analysis the designs structure on all proposed design parameters were conducted.

For the second stage is designing process of the MOSFET. These designs were constructed by using Silvaco TCAD software. The criterion of all three gate length designs based on the structure of ITRS is proposed as the suitable parameters. The first step in this process is by designing the MOSFET by using the Silvaco's DEVEDIT software. All the dimension sizes are set according to the parameters that will be tested. Then, the base region and the desired impurities are being doped into the structure. For the shallow source/drain extension, the structure is the same as the ITRS structure but only modification is made to the junction depth of source/drain extension that it becomes shallower. Subsequently, the MOSFET is tested, simulated and executed in the Silvaco's ATLAS software. Here, the desired graphs are plotted by Tonyplot software. From the graphs obtained, threshold voltage ( $V_{TH}$ ) and "ON" current ( $I_{ON}$ ) are extracted. Finally, analysis in improving SCE for the design structure was carried out. The standard structure (ITRS) and shallow source/drain extension structure are also compared.

## III. RESULT AND ANALYSIS

### A. Parameter design

Table 1 shows the parameter for design shallow source/drain extension structure. The Silvaco's DEVEDIT software is used to design the structure by referring to the parameters. The structures MOSFET design is shown in Figure 1-6.

### B. Graphs Transfer Curves ID against VGS for Shallow Source/Drain Extension (SDE) Profiles Structure

Figure 7-12 shows the graphs of Transfer Curves ID against  $V_{GS}$  for Shallow Source/Drain Extension (SDE) Profiles Structure. From these graphs, we can obtained the

value of threshold voltage,  $V_{TH}$  for drain voltage,  $V_{DS}$  0.7V and 50mV for the gate length 24nm, 16nm and 9.8nm.

Table 1  
Overall Parameter for Shallow Source/Drain Extension (SDE) Structure with Gate Length 24nm, 16nm and 9.8nm

Parameters	Physical Gate Length		
	24 nm	16 nm	9.8 nm
Power Supply Voltage (V)	0.7	0.61	0.51
Channel Doping (Boron) ( $10^{18} / \text{cm}^3$ )	3.7	0.1	0.1
Silicon Dioxide ( $\text{SiO}_2$ ) Thickness (nm)	0.9	0.8	0.7
Junction Depth ( $X_j$ ) (nm)	5.0	4.0	3.0
Base Impurities (Arsenic) ( $10^{19} / \text{cm}^3$ )	1.0	1.0	1.0
MOSFET Body Dimension (nm)	80 x 20	80 x 20	80 x 20
Source/Drain Electrode Dimension (nm)	15 x 2	15 x 2	15 x 2




Figure 3: MOSFET design with 16nm gate length




Figure 4: Contour structure with junction depth for 16nm gate length MOSFET design




Figure 1: MOSFET design with 24nm gate length




Figure 5: MOSFET design with 9.8nm gate length




Figure 2: Contour structure with junction depth for 24nm gate length MOSFET design




Figure 6: Contour structure with junction depth for 9.8nm gate length MOSFET design




Figure 7:  $I_D - V_{GS}$  curves of 0.7V drain voltage for 24nm gate length MOSFET




Figure 10:  $I_D - V_{GS}$  curves of 50mV drain voltage 16nm gate length MOSFET




Figure 8:  $I_D - V_{GS}$  curves of 50mV drain voltage 24nm gate length MOSFET




Figure 11:  $I_D - V_{GS}$  curves of 0.7V drain voltage 9.8nm gate length MOSFET




Figure 9:  $I_D - V_{GS}$  curves of 0.7V drain voltage for 16nm gate length MOSFET




Figure 12:  $I_D - V_{GS}$  curves of 50mV drain voltage 9.8nm gate length MOSFET

C. Graphs Subthreshold Curves Log  $I_D$  against  $V_{GS}$  with 50mV and 0.7V drain voltages for Source/Drain Extension (SDE) Profiles Structure

Figure 13-15 shows the graph of Subthreshold Curves Log  $I_D$  against  $V_{GS}$  with 50mV and 0.7V drain voltages for Source/Drain Extension (SDE) Profiles Structure. From these graphs, we can get the value of "ON" current,  $I_{ON}$  for drain voltage,  $V_{DS}$  0.7V and 50mV with the gate length 24nm, 16nm and 9.8nm.

D. Comparison of the  $V_{TH}$  value between three Gate Lengths for Standard Structure (ITRS) with Shallow Source/Drain Extension (SDE) Profiles

For the shallow source/drain extension (SDE) profiles structure from DEVEDIT, the Figure 16 shows that the value of  $V_{TH}$  is increases from the standard structure (ITRS). When the short-channel effect reduces, the value of the  $V_{TH}$  will increase. In theory, the shorter the length gate, the value of the  $V_{TH}$  becomes lower [6]. Analysis for the  $V_{TH}$  shows that when the junction depth of SDE MOSFET becomes shallower, the  $V_{TH}$  increases. For  $V_{DS} = 0.7V$ , it was found that the  $V_{TH}$  increases by 40.08% when the junction depth,  $X_j$  reduces from 9nm to 5nm for gate length 24nm. For gate length 16nm, the  $V_{TH}$  increases by 80.49% when the junction depth,  $X_j$  reduces from 6nm to 4nm, while  $V_{TH}$  increases by 65.48% when the junction depth,  $X_j$  reduces from 3.7nm to 3nm for length gate 9.8nm.

Meanwhile, for  $V_{DS} = 50mV$ , it was found that the  $V_{TH}$  increases by 52.54% when the junction depth,  $X_j$  reduces from 9nm to 5nm for gate length 24nm. For gate length 16nm, the  $V_{TH}$  increases by 114.08% when the junction depth,  $X_j$  reduces from 6nm to 4nm, while  $V_{TH}$  increases by 36.49% when the junction depth,  $X_j$  reduces from 3.7nm to 3nm for length gate 9.8nm.

All the shallow source/drain extension structure MOSFET shows increases value of  $V_{TH}$ . Thus, the scaling the junction depth solved and improved the short-channel effect.

E. Overall Outputs

Table 2 shows the results for the overall output from the graph for  $V_D=0.7V$  and 50mV at the gate length 24nm, 16nm and 9.8nm before reducing the junction depth,  $X_j$  which are 9nm, 6nm and 3.7nm. The measurement output including the threshold voltage,  $V_{TH}$  and maximum current,  $I_{ON}$  from the graph.

Figure 18 shows the results for the overall output from the graph for  $V_D=0.7V$  and 50mV at the gate length 24nm, 16nm and 9.8nm after reduce the junction depth,  $X_j$ . The measurement output including the threshold voltage,  $V_{TH}$  and maximum current,  $I_{ON}$  from the graph.

IV. CONCLUSION

After finishing the studies, this project can be concluded that the design shallow source/drain extension (SDE) profiles is one of the alternatives in improving short channel effect. The element in designing shallow source/drain extension (SDE) profiles is decreasing the scale of junction depth,  $X_j$  from the standard structure (ITRS) NMOS transistor. This scaling modification also improves the performance on the NMOS transistor in nanoscale devices by having lower power consumption




Figure 13: Log  $I_D - V_{GS}$  subthreshold curves with 50mV and 0.7V drain voltage for 24nm gate length MOSFET




Figure 14: Log  $I_D - V_{GS}$  subthreshold curves with 50mV and 0.7V drain voltage for 16nm gate length MOSFET




Figure 15: Log  $I_D - V_{GS}$  subthreshold curves with 50mV and 0.7V drain voltage for 9.8nm gate length MOSFET




Figure 16: Graph Gate length, L<sub>G</sub> against V<sub>TH</sub> for standard structure (ITRS) and source/drain extension (SDE) profiles structure and standard structure (ITRS)

Table 2  
Overall Output Data for Source/Drain Extension (SDE) Profiles Structure Before Reducing the Junction Depth

	V <sub>DS</sub>	Gate Length		
		24nm	16nm	9.8nm
Threshold Voltage, V <sub>TH</sub> (V)	0.7 V	0.2914	0.1358	0.1043
	50 mV	0.1928	0.1087	0.1003
Maximum Current, I <sub>ON</sub> (A)	0.7 V	9.39024 x 10 <sup>-5</sup>	2.09029 x 10 <sup>-6</sup>	3.61309 x 10 <sup>-7</sup>
	50 mV	9.87347 x 10 <sup>-6</sup>	1.71038 x 10 <sup>-7</sup>	4.27614 x 10 <sup>-8</sup>

Table 3  
Overall Output Data for Source/Drain Extension (SDE) Profiles Structure After Reducing the Junction Depth

	V <sub>DS</sub>	Gate Length		
		24nm	16nm	9.8nm
Threshold Voltage, V <sub>TH</sub> (V)	0.7 V	0.4082	0.2451	0.1726
	50 mV	0.2941	0.2327	0.1369
Maximum Current, I <sub>ON</sub> (A)	0.7 V	1.33147 x 10 <sup>-6</sup>	9.10737 x 10 <sup>-7</sup>	3.9711 x 10 <sup>-8</sup>
	50 mV	1.08512 x 10 <sup>-7</sup>	6.37642 x 10 <sup>-8</sup>	3.82581 x 10 <sup>-9</sup>

The shallow source/drain extension (SDE) profiles have been designed virtually using TCAD Silvaco software. DEVEDIT in Silvaco software is used in this project to design the NMOS transistor and scaling the junction depth, X<sub>j</sub> for shallow source/drain extension profiles. Besides, the ATLAS in Silvaco software is used to simulate the structure of design to obtain the outputs and graphs. Based on the simulation analysis, the threshold voltage, V<sub>TH</sub> for shallow source/drain extension profiles slightly increase from the standard structure (ITRS) gate length 9.8nm, 16nm and 24nm when drain voltage is 50mV and 0.7V. The I<sub>ON</sub> of both structure have a different values. I<sub>ON</sub> shows the active region for the transistor. In theory, for shorter gate length, L<sub>G</sub>, the threshold voltage, V<sub>TH</sub> will decrease. The value of the V<sub>TH</sub> from the output proved that the shallow source/drain extension profiles improve the short-channel effect.

ACKNOWLEDGMENT

The authors would like to thank the Universiti Teknikal Malaysia Melaka and lecturers for support given through the research.

REFERENCES

- [1] Yannis T., The MOS Transistor. 2nd Edition, McGraw Hill, 1999.
- [2] Muller R. S., Kamins T. I., Device Electronics for Integrated Circuits, John Wiley and Sons, 1977.
- [3] D'Agostino F., and Quercia D., Short-Channel Effects in MOSFETs, 2000
- [4] Thompson S. et al. "Source/Drain Extension Scaling For 0.1µm And Below Channel Length MOSFETs," *VLSI Technology in Proc. Symp.*, 132-133, 1998.
- [5] Bohr M., Ahmed S.S., Ahmed S.U., Bost M., Ghani T., Greason J., Hainsey R., Jan C., Packan P., Sivakumar S., Thompson S., Tsai J., and Yang S. 1996. IEDM Technical Digest. 847.
- [6] Yuan Taur and Tak H. N., Fundamentals of Modern VLSI Devices. Cambridge University Press, 2013.
- [7] Scott Thompson, Paul Packan, and Mark Bohr, "MOS Scaling: Transistor Challenges for the 21st Century," *Intel Technology Journal*, 1998.
- [8] Campbell S.A., Gilmer D.C., Wang X.C., Hsieh M. T., Kim H.S., Gladfelter W.L., and Yan J. *IEEE Electron Device*, pp. 104, 1997.
- [9] Nishida M. and Onodera H, "An Anomalous Increase Of Threshold Voltage With Shortening The Channel Lengths For Deeply Boron-Implanted N-Channel MOSFET's," *IEEE Trans. Electron Devices*, no. 28, pp. 1101, 1981.
- [10] Okumura Y., Shirahata M., Okudaira T., Hachisuka A., Arima H., Matsukawa T., and Tsubouchi N, "A Novel Source-To-Drain Nonuniformity Doped Channel (NUDC) MOSFET for High-Current Drivability And Threshold Voltage Controllability," *IEEE IEDM Tech. Dig.*, no. 391, 1990.